



## Filtech Data Sheet 4152

Grade	4152
Weight (g/m <sup>2</sup> )	154
Thickness (mm)	0.58
Flow Rate – (ml/min)	475
- Hertzberg (sec/100ml)	15
Wet Burst Strength (mm H <sub>2</sub> O)	2794
Capillary Rise (mm/min)	N/D
Retention (µm)	31
Loading Capacity	Very High
Surface	Creped

### Grade Characteristics :

#### Qualitative Filter Paper - High Wet Strength Grade

Filtech Grade 4152 is used in many industrial applications and mining labs. This is a very economical grade offering fast flow rate, good retention and strength. Creped surface. Very thick material.

NOTE: Specifications given are typical values that fall within a defined range. For this reason observed values may vary slightly

\*\* Samples available upon request