



Filtech Data Sheet 4332

Grade	4332
Weight (g/m ²)	70
Thickness (mm)	0.27
Filtration time for 10ml distilled water(s)	18.0
- Hertzberg (sec/100ml)	400
Wet Burst Strength (mm H ₂ O)	>60
Capillary Rise (mm/min)	5
Retention (µm)	10
Air Resistance (mbar)	7
Surface	Creped

Grade Characteristics : Qualitative Filter Paper

Filtech Grade 4332 offers an economical version of Filtech Grade 1845. Grade 4332 is an excellent paper for use in the sugar industry in terms of both performance and cost.

NOTE: Specifications given are typical values that fall within a defined range. For this reason observed values may vary slightly

** Samples available upon request