



Filtech Data Sheet 486

Grade	486
Weight (g/m ²)	67
Thickness (mm)	0.33
Flow Rate – (ml/min)	120
Filtration Speed - Hertzberg (sec/100ml)	57
Wet Burst Strength (mm H ₂ O)	279
Retention (µm)	1.1
Loading Capacity	Very High

Grade Characteristics : Glass Fibre Filter Paper

Filtech Grade 486 is very similar to Grade 483, with higher wet strength and low metals content. Recommended for analysis of tradewaste samples. Grade 486 is also recommended for environmental air monitoring applications. 99.999% DOP retention. (**low metals grade**)

NOTE: Specifications given are typical values that fall within a defined range. For this reason observed values may vary slightly

** Samples available upon request